

TABLE REGULATION OF DYNAMICA MACHINE

Fabric Knit Cotton COT/PES-Lycra	weight gr/lin.mt	PUMP Rpm	IDROVARIO POSITION	REEL SPEED FULL LOAD m/min	ROPE TIME sec.	ABSORPTION %	BAGNO LAVORO VB	Liquor Ratio Full load kg		LOAD %
								MIN	MAX.	
Jersey - Interlock ***	180>200	1150	25%	260-280	135-145	2,2 - 2,5	1,5	3,7	4,5	100%
Piquet Jersey-rib-interlock***	220-250	1200	25%	260-280	120-130	2,5 - 2,7	1,5	4	4,2	100%
Piquet Jersey-rib-interlock	250-350	1250	40%	250-270	160-180	2,5 - 3	1,5	4	4,5	100%
Piquet Jersey-rib-interlock	>350	1350	60%	240-250	150-160	2,5 - 3	2	4,5	5	100%
French terry Heavy Co or Co/pes	<400	1350	60%	230-250	140-150	2,5 - 3	2	4,5	5	100%
French terry Heavy Co or Co/pes	>480 max.	1350	60%	210-230	120-130	2,5 - 3	2	4,5	5	90%
Co/Ea	260-300	1200	40%	280-300	160-170	2.5 - 3	2	4,5	5	90%
Co/Ea	300-350	1250	60%	250-270	150-160	2.5 - 3	2	4,5	5	90%
Co/Ea	350-400	1350	60%	230-250	140-150	2,5 - 3	2	4,5	5	90%
Modal/Viscose/Ea	< 240	1150	40%	max 270	160-180	2 - 2,5	2,5	4,5	5	80%
Modal/Viscose/Ea	240-280	1200	60%	max 260	150-165	2 - 2,5	2,5	4,5	5	80%
Modal/Viscose/Ea	280-320	1250	60%	max250	140-140	2 - 2,5	2,5	4,5	5	80%
Co O.E Piquet Jersey-interlock	220-250	1250	25%	300-320	170-180	2,2 - 2,5	1,5	3,7	4	100%
Co O.E Piquet Jersey--interlock	300-350	1300	40%	260-280	160-170	2,5 - 3	1,5	4	4,5	100%
Co O.E Piquet Jersey--interlock	350-400	1350	60%	240-260	140-150	2,5 - 3	2	4,5	5	100%
Co O.E Piquet Jersey--interlock	>400	1350	60%	230-240	130-140	2,5 - 3	2	4,5	5	95%
Piquet Jersey--interlock 20/1-20/2	230-250	1300	40%	290-310	170-180	2,5 - 3	1,5	4	4,5	100%
Piquet Jersey--interlock 20/1-20/2	280-330	1350	40%	270-290	150-160	2,5 - 3	1,5	4	4,5	100%
Jersey pes.	250-300	1300	20%	300-320	130-140	2 - 2,5	2	4	4,5	85%

*** LOADING IN DOUBLE ROPE

Be aware that values reported in the chart are approximate and valid for the percentage of the nominal loading of the machine reported in the last column only